

Makrolon® Vista QX

Solid polycarbonate sheet



I Line
Innovative

Your benefits:

- enhanced optical quality
- extreme impact strength
- resistance to a wide range of temperatures

Solid **Makrolon® Vista QX** sheets are clear, polished polycarbonate sheets with enhanced optical properties. They offer extreme impact strength that exceeds the physical properties of other products of their class. **Makrolon® Vista QX** sheets resist temperatures of -100 to +120 °C, exhibit high optical clarity and have good fire properties. The sheets offer protection against involuntary breakage and willful destruction.

Makrolon® Vista QX sheets can be thermoformed, cold-curved and machined with ease.

Applications:

Typical applications for **Makrolon® Vista QX** include glazing in automotive, such as windows and panoramic roofs, where low weight or high impact resistance is required – like in electrical cars, heavy duty vehicles or police cars. Other possible applications include visors, machine guards, coated sheets and lamination with glass.

	Test Conditions	Typical values ⁽¹⁾	Unit	Standard
Physical				
Density		1200	kg/m ³	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	–	ISO 489
Mechanical				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Nominal strain at break	50 mm/min	> 50	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m ²	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm, notched	80P	kJ/m ²	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	90P	kJ/m ²	ISO 180-A
Thermal				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(mK)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 ⁻⁴ /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2
Electrical				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	–	IEC 60250
Relative permittivity	1 MHz	3.0	–	IEC 60250
Dissipation factor	100 Hz	5 10 ⁻⁴	–	IEC 60250
Dissipation factor	1 MHz	95 10 ⁻⁴	–	IEC 60250

⁽¹⁾ These values are measured on injection molded samples, and are not intended for specification purposes.

Makrolon® Vista QX

Solid polycarbonate sheet



Ideas, innovative, intelligent, interesting... Covestro i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Light Transmission: Test Method according to DIN EN ISO 13468-2.

The stated thicknesses are not all available as standard. Please ask us for more information. The stated values are typical values only.

Light transmission %	3	4	5	6	8	10	12
Makrolon® Vista QX clear 099	88	87	87	86	85	83	82

Available sizes:

Makrolon® Vista QX7 and QX90 are available in thicknesses of 3 – 12 mm and Makrolon® Vista QX10 and QX200 in thicknesses of 3 – 8 mm.
Other sizes and sheet thicknesses on request.

Sizes (standard):

3,050 x 2,050 mm

Permanent Service Temperature: The permanent service temperature without load is approx. 120 °C.

Available types:

Performance on	Vista QX7	Vista QX10	Vista QX90	Vista QX200
Inclusions/black spots	++	++	++	++
Surface quality/ transparent defects	+	++	+	++
Diopter	-	-	++	++

Makrolon® Vista QX7 and QX90 are suitable for applications which will be hard coated afterwards.

Makrolon® Vista QX10 and QX 200 have a further enhanced surface quality, for high level applications.

Please contact us for more detailed specifications.



Covestro Deutschland AG
Business Unit Polycarbonates
51365 Leverkusen
Germany

www.sheets.covestro.com
sales.sheets.EMEA@covestro.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark of Covestro AG